

Charge Transport through a Single Molecule of *trans*-1-bis-Diazafluorene [60]fullerene

Davide Stefani,^{†,‡,§} Cristian A. Gutiérrez-Cerón,^{†,§} Daniel Aravena,^{||,§} Jacqueline Labra-Muñoz,[⊥] Catalina Suarez,[#] Shuming Liu,^{#,▲} Monica Soler,[△] Luis Echeгойen,[#] Herre S.J. van der Zant,[‡] and Diana Dulić^{*,§}

[‡]Kavli Institute of Nanoscience, Delft University of Technology, Lorentzweg 1, Delft 2600 GA, The Netherlands

[§]Department of Physics, Faculty of Physical and Mathematical Sciences and [⊥]Department of Electrical Engineering, Faculty of Physical and Mathematical Sciences, University of Chile, Avenida Blanco Encalada 2008, Santiago 8330015, Chile


^{||}Department of Material Chemistry, Faculty of Chemistry and Biology, University of Santiago de Chile, Casilla 40, Correo 33, Santiago 9170022, Chile

[#]Department of Chemistry, University of Texas, 500 West University Avenue, El Paso, Texas 79968, United States

[△]Department of Material Science, Faculty of Physical and Mathematical Science, University of Chile, Avenida Beauchef 851, Santiago 8330015, Chile

Supporting Information

ABSTRACT: Fullerenes have attracted interest for their possible applications in various electronic, biological, and optoelectronic devices. However, for efficient use in such devices, a suitable anchoring group has to be employed that forms well-defined and stable contacts with the electrodes. In this work, we propose a novel fullerene tetramalonate derivate functionalized with *trans*-1,4,5-diazafluorene anchoring groups. The conductance of single-molecule junctions, investigated in two different setups with the mechanically controlled break junction technique, reveals the formation of molecular junctions at three conductance levels. We attribute the conductance peaks to three binding modes of the anchoring groups to the gold electrodes. Density functional theory calculations confirm the existence of multiple binding configurations and calculated transmission functions are consistent with experimentally determined conductance values.



INTRODUCTION

For many years, a wide variety of fullerene derivatives has been reported and their potential applications as electronic, magnetic, catalytic, biological and optical materials have been explored.^{1–7} In particular, C₆₀ and its derivatives are ideal candidates for molecular-based devices because of their interesting and unique electronic properties.^{8,9} One of the long-standing challenges in obtaining functional molecular electronic devices is the transport of electrons through single molecules,^{10,11} i.e., it is necessary to guarantee molecular conduction through a single molecule rather than through a group of molecules.¹² The electron transport properties of single molecules can then be controlled electrically, magnetically, optically, mechanically, or chemically to obtain the desired functionality.¹³ However, in the case of fullerene derivatives, the groups used to functionalize the carbon cage may also modify the electronic properties of the molecule.¹⁴ In addition, the molecule needs to possess anchoring groups that will form well-defined and stable molecular junctions with the electrodes.^{15–17} Therefore, the orientation and nature of the anchoring groups will affect the charge transport properties of the molecule. Finding a suitable anchoring group to connect

C₆₀ electrically would be an important step toward more interesting derivatives in the future.

Charge transport in pristine C₆₀ has been studied for a long time using both scanning tunnelling microscope break junction (STM-BJ)^{18,19} and mechanically controlled break junction (MCBJ)^{20,21} techniques and conductance values around 0.1 G₀ have been reported; here G₀ is the quantum of conductance equaling $2e^2/h = 77.48 \mu\text{S}$.^{22,23} Taking advantage of its affinity for metals, Martin et al.²⁴ studied a “dumbbell” benzene-difullerene (BDC60) derivate in which C₆₀, at both ends of the molecule, acts as the anchoring group. The single peak of conductance found at $3 \times 10^{-4} G_0$ for this derivate was attributed to a transport-limiting barrier created by the nitrogen atoms of the pyrrolidine rings that are connected to the benzene backbone.²⁵ An analogous work with a dumbbell fullerene molecule reported a conductance peak around $1 \times 10^{-4} G_0$ confirming the low conductance values for functionalized fullerenes.²⁶ Additionally, in these studies there is no evidence of a direct electronic transfer through only one of the

Received: May 18, 2017

Revised: July 28, 2017

Published: August 3, 2017




Figure 1. (a) Schematics of the MCBJ devices used in the experiment.³⁷ (b) Chemical structure of the *trans*-1-bis-diazofluorene adduct of C_{60} -tetramalonate (C_{60} -daf). Malonates are designated with red balls representing the $C(\text{COOC}_2\text{H}_5)_2$ groups.




Figure 2. (a) Two-dimensional conductance histogram built from a selection of the 10,000 consecutive breaking traces recorded after drop-casting the solution containing C_{60} -daf. Traces that had 1.2 times the average amount of counts between 1×10^{-4} and $1 \times 10^{-6} G_0$ were selected (24.2% of the total). The inset shows the traces that were not selected (i.e., that have less than 1.2 times the average count in the region under consideration, 75.8%). The breaking traces have been logarithmically binned in the conductance axis with 49 bins/decade and with 58.4 bins/nm in the displacement axis. The applied bias voltage is 0.1 V and the electrode speed is 4.0 nm/s. (b) Individual breaking traces in the presence of a C_{60} -daf molecule. Traces are offset along the x -axis by 1.5 nm for clarity. (c) Normalized one-dimensional histograms obtained by integrating the breaking traces along the displacement axis. The red line represents the histogram obtained for the selected traces, the green line from the excluded traces, and the blue line shows the histogram of the whole data set. The dashed black line represents the log-normal fit to the selected histogram (red line). Experiment conducted in Delft, The Netherlands.

fullerene anchoring groups. Nevertheless, a more recent study of a dumbbell fullerene derivative shows two different electronic transport configurations, one assigned to the transport through the molecular bridge and the second, at higher conductance values, ascribed to a single C_{60} anchoring group trapped between the two adjacent electrodes.²⁷ These two peaks differ by 2 orders of magnitude ($1 \times 10^{-1} G_0$ and $1 \times 10^{-3} G_0$), which is consistent with the previous reported values for pristine C_{60} fullerenes^{18–21} and dumbbell C_{60} fullerene

derivatives.^{24–26,28} We can also find theoretical studies that support these results^{29,30} and experimental studies of other C_{60} fullerene derivatives, i.e., amino-terminated derivatives.³¹

In this work, we study the molecular conductance through single-molecule junctions of a C_{60} fullerene all-equatorial tetramalonate derivate functionalized with *trans*-1,4,5-diazo-fluorene anchoring groups³² (see structure in Figure 1b and hereafter denoted as C_{60} -daf for convenience). The diazo-fluorene anchoring groups are perfectly perpendicularly




Figure 3. (a) Two-dimensional conductance histogram built from a selection of the 5,000 consecutive breaking traces recorded after drop-casting the solution containing C_{60} -daf. Traces that had 1.2 times the average amount of counts between 1×10^{-4} and $1 \times 10^{-6} G_0$ were selected (29.6% of the total). The inset shows the traces that were not selected (i.e., that have less than 1.2 times the average count in said region, 70.4%). The breaking traces have been logarithmically binned in the conductance axis with 49 bins/decade and with 88.4 bins/nm in the displacement axis. The applied bias voltage is 0.1 V and the electrode speed is 6.0 nm/s. (b) Normalized one-dimensional histograms obtained by integrating the breaking traces along the displacement axis. The red line represents the histogram obtained for the selected traces, the green line from the excluded traces, and the blue line shows the histogram of the whole data set. The dashed black line represents the log-normal fit to the selected histogram (red line). Experiment conducted in Santiago de Chile, Chile.

oriented with respect to the fullerene surface, and linearly disposed with respect to each other. Four equatorial diethyl malonate groups were added to the C_{60} to avoid direct interactions between the gold electrodes and the fullerene cage. The ethyl esters in these groups have high contact resistance and low binding energy to gold, which effectively renders them bulky groups that block access to the C_{60} cage.³³ This aspect and the evidence of direct coordination between the diazafluorene groups and many metal ions^{32,34} suggest that the formation of a molecular junction occurs only through a linear arrangement of diazafluorene groups and the gold electrodes. Such a junction structure allows the study of charge transport through the carbon cage of the fullerene derivative. The computational simulations performed indeed show preferential binding of the nitrogen atoms to the gold leads and that the highest occupied molecular orbital (HOMO) is sufficiently well communicated to allow the electronic transfer.

Because one of the biggest challenges in molecular electronics field is to have comparable and reproducible results between different techniques, instruments, or data sets, we have performed our experiments in two identical MCBJ setups located in two different laboratories in Delft and Santiago de Chile.

To the best of our knowledge, the diazafluorene group has never been tested as an anchoring group before.^{35,36} In addition, charge-transport studies using a C_{60} derivative with *trans*-1 terminal groups to form molecular junctions with gold electrodes have not been reported.

RESULTS AND DISCUSSION

The conductance of C_{60} -daf (Figure 1b) was measured in air at room temperature. Both MCBJ setups (the setups are copies and made in Delft/Leiden) and the measuring technique have been extensively described elsewhere.^{37,38} To fabricate the MCBJ devices (Figure 1a), we used e-beam lithography to deposit a gold wire with a thin (<100 nm wide) constriction on a bendable substrate. The substrate is then bent by driving a

pushing rod onto its middle part while keeping its edges clamped. This causes the gold wire to stretch until a single gold atom connects the two extremities. Further bending results in a breaking of the wire forming two sharp electrodes. The single-gold atom termination can be observed in a conductance vs electrode displacement trace (breaking trace) as the formation of a plateau around $1 G_0$. A sudden drop in conductance to about $1 \times 10^{-3} G_0$ signals the rupture of the gold wire. This point is defined as the zero displacement ($d = 0$) in a breaking trace. After the initial opening of the junction, the electrodes are moved apart and the conductance is recorded until the noise level is reached. When this sequence is finished, the electrodes are fused back together until the conductance is above $30 G_0$ and the whole process is repeated.

We start each experiment by characterizing the bare device. We apply a bias voltage of 0.1 V to the gold wire and measure the current passing through it while repeatedly opening and closing the junction. A device is used for molecule measurements only if it shows just vacuum tunneling and a clear single-gold atom, $1 G_0$ plateau.³⁹ An $\sim 30 \mu\text{M}$ solution with the molecules under investigation is prepared by dissolving the starting compound in dichloromethane. Two $2 \mu\text{L}$ droplets of the solution are subsequently drop-cast on the freshly characterized device.

A data set is composed of thousands of consecutive breaking traces from individual junctions recorded with the same settings and is used to construct a 2D conductance histogram (conductance vs electrode displacement).³⁹ By integrating over the displacement, a one-dimensional histogram is obtained, from which the most probable junction conductance is usually estimated. To facilitate the identification of molecular traces, a homemade MatLab program is used to select traces that have high counts in the conductance region of interest. The filtering method is based on the fact that if a molecule is not trapped in the junction the conductance decreases exponentially; the corresponding breaking trace therefore does not display many counts in the high-conductance region.

Table 1. Comparison of the Fitting Parameters Obtained from the Measurements in Delft and Santiago de Chile^a

peak	Delft			Santiago de Chile		
	μ ($\times 10^{-5} G_0$)	p	w	μ ($\times 10^{-5} G_0$)	p	w
A	2.3 (2.3)	-4.7 (-4.6)	0.6 (0.5)	3.1 (2.8)	-4.5 (-4.6)	0.6 (0.6)
B	0.79 (0.87)	-5.2 (-5.1)	0.5 (0.7)	0.77 (0.82)	-5.1 (-5.1)	0.6 (1.3)
C	0.18 (0.12)	-5.8 (-5.9)	0.9 (1.7)	0.17 (0.16)	-5.8 (-5.8)	0.6 (0.4)

^aThe \log_{10} of the peaks found in the one-dimensional conductance histogram after data filtering were fitted to a triple-log normal ($y = he^{-\left(\frac{\log_{10}(G/G_0)p}{w}\right)^2}$), where p is the peak maximum expressed in $\log_{10}(G/G_0)$, μ is the corresponding conductance in G_0 , w is the full-width-half-maximum of the peak expressed in $\log_{10}(G/G_0)$, and h is the peak height (not displayed in the table). The results obtained from two other samples are included within parentheses. The conductance histograms of these samples are shown in the [Supporting Information](#).

The filtering procedure can also be used to estimate the percentage of junctions that contain a molecule. To construct the 2D histogram in [Figure 2a](#), we used the following criterion: traces that have 1.2 times the average amount of counts in the 1×10^{-4} to $1 \times 10^{-6} G_0$ region are selected. The inset in the same figure displays the traces that did not satisfy the requirements and were therefore excluded from the selection. The sum of these two histograms thus constitutes the complete data set, which can be found in [Figure S1](#). We have furthermore verified that when adjusting the filtering criteria the main conclusions of the paper do not change (see [Figures S4 and S5](#)).

The 2D histogram in [Figure 2a](#) shows a high-count region around $1 \times 10^{-5} G_0$, which extends up to 1.5–2 nm. The counts are concentrated mostly around two values and a log-normal fit of the one-dimensional histogram ([Figure 2c](#)) indicates that the corresponding most probable conductance values are 2.3×10^{-5} (peak A) and $7.9 \times 10^{-6} G_0$ (peak B). The individual breaking traces show that the plateaus can (traces i and ii in [Figure 2b](#)) but do not always appear together (trace iii). Some breaking traces also show a third plateau around $2 \times 10^{-6} G_0$ (traces iv and v in [Figure 2b](#)), but their appearance is not as frequent. Including this third peak in the fitting increases the accuracy of the fit and yields a conductance value of 1.8×10^{-6} for peak C.

The experiment has been repeated in Santiago de Chile by the group of D. Dulić. [Figure 3a](#) shows the two-dimensional histogram obtained from a selection of the 5000 traces collected (same criterion as used in [Figure 2a](#); a histogram made from the rest of the traces is shown in the inset). The same bias voltage of 0.1 V as in Delft was used, but the electrode speed was one and a half times higher in this case. The plot confirms the same high-count region near $1 \times 10^{-5} G_0$, displaying a striking resemblance with the one measured in Delft. In addition, the histogram measured at Santiago de Chile more clearly shows the high counts in the low-conductance region, centered around $2 \times 10^{-6} G_0$ and extending to lengths of 1.5 nm. The one-dimensional histogram ([Figure 3b](#)) highlights this area with a peak in conductance, from which the most probable conductance value of $1.7 \times 10^{-6} G_0$ (peak C) is obtained. The log-normal fit of the higher conductance region yields 3.1×10^{-5} (peak A) and $7.7 \times 10^{-6} G_0$ (peak B), values which are close to those found in the measurements performed in Delft.

From the conductance histograms in [Figures 2 and 3](#) it is evident that peak A represents the most probable formation of molecular junctions in both measurements. The measurements obtained in Delft show the presence of peak B more clearly, whereas peak C is more pronounced in the measurements from Santiago de Chile. A comparison between the fit results

obtained from fitting the data set acquired in Delft and in Santiago de Chile is presented in [Table 1](#). The values obtained from two other samples are also included within parentheses, with the corresponding conductance histograms shown in [Figure S2 and S3](#). The conductance values for the three peaks obtained in Delft and in Santiago de Chile match very well. The width (w) of peaks A and B is very similar in both cases, whereas that of peak C is different. We attribute this difference to the difficulty of fitting peak C in the sample obtained in Delft. A more refined data selection shown in the [Supporting Information](#) shows an improved fitting of this peak ([Figure S4](#)). Furthermore, peak A is more prominent in the measurements from Santiago de Chile, while its importance is less striking in those from Delft. This is true for all samples except the one presented in the [Figure S3](#). Peak C is the smallest one in all measurements.

Recently, Seth et al.⁴⁰ studied the conductance through a bisterpyridine derivative with the MCBJ technique, finding that multiple configurations that display short plateaus are accessible for charge-transport with the conductance spanning several orders of magnitude. Although we could expect a similar behavior from the diazafluorene group, the number of accessible conductance configurations should be less because of the reduced number of nitrogen atoms. Moreover, the C_{60} and malonate groups contribute to the rigidity of the molecule, resulting in more stable conductance plateaus, as clearly shown in the data presented in [Figures 2 and 3](#). We tested the behavior of this molecule in our setup and to be able to do a more accurate comparison with the previous result we measured its single-molecule conductance. In this case we did not observe well-defined conductance values (see [Figure S6](#)), again suggesting that the presence of the C_{60} molecular bridge plays an important role in obtaining well-defined molecular junctions. Moreover, the additional nitrogen binding site could provide configurations with more similar conductance to each other, thus hindering their identification.

Although the measurements cannot directly discard the involvement of the aromatic rings in the diazafluorene units in the charge transport, if they were involved, we would expect a more continuous decrease in conductance instead of the steplike plateaus observed in the breaking traces. The more continuous decay would in turn result in a broader distribution of the conductance values instead of the agglomeration around only three separate values, each with a variance comparable to that of other experiments that employ amino anchoring groups.^{41,42}

To gain additional insight into the binding configurations of C_{60} -daf, ab initio density functional theory calculations have been performed. The transmission function $T(E)$ at zero bias was calculated using the B3LYP functional (see Computational




Figure 4. (a) Au–N distance (blue and red lines) and total energy (black line) at each step of the surface scan of the diazafluorene-Au₂₀ model. Snapshots of a two and one N-coordinated geometry are depicted in the graphic. (b) Potential energy surface for the Au–H interaction.




Figure 5. Transmission function for the different binding models. The line color represents the number of Au–N bonds at one gold tip and the line style represents the binding mode at the other end. The solid black line indicates binding by two N atoms at each side. The dashed red line indicates binding by one N atom at each diazafluorene anchoring group and the gray dotted line indicates a Au–H van der Waals contact at each side. Mixed colors and line styles mean mixed binding modes. For instance, a dashed gray line corresponds to a Au–H contact on one tip (for the gray color) and one N binding on the opposite side (dashed line). The Fermi level is located at 0 eV and is indicated by a horizontal dashed line.

Details section for a detailed description of the computational methodology). To consider the different binding modes of the diazafluorene group, a geometry optimization of this anchoring group and a Au₂₀ cluster was performed. The lowest energy conformation corresponds to a geometry in which the Au₂₀ cluster is coordinated to the two N-donor atoms with a distance of ca. 2.45 Å. A relaxed surface scan was then run, elongating the distance between the top Au atom and the central C atom of the diazafluorene moiety (position 9 of the fluorene moiety, see Figure 4). As the distance constraint is not defined with respect to the Au–N distance, the nitrogen atoms are free to accommodate their position with respect to the gold tip during the scan.

A clear rupture of one of the Au–N bonds occurs at a Au–C(9) distance of 5.35 Å, when one of the Au–N bonds remains short (blue line), whereas the other is markedly longer (red line) (Figure 4a). Considering the orientation change of the

diazafluorene group during the breaking of the Au–N contacts, it is also convenient to explore the possibility of a van der Waals contact between the Au and the H atoms in the diazafluorene. Such interactions can yield additional low-conductance peaks and have been identified in molecular junctions with thiophene anchoring groups.⁴³ In this way, a second surface scan was performed; this time by elongating the Au–H distance (see Figure 4b). A clear minimum is observed at 2.18 Å when using a dispersion corrected density functional (D3 correction and BP86 functional). The corresponding Au–C(9) distance is 7.49 Å in this conformation.

The three binding motifs can be combined to yield nine different anchoring patterns to the gold tips: ranging from a strongly bonded geometry where both diazafluorene groups are bonded through their two N atoms, to a weakly bonded case with two Au–H interactions. Regardless of the specific binding mode, all calculations show a relatively large band gap (>3 eV),

where the LUMO orbital tends to be closer to the Fermi level (between 1 and 1.5 eV above E_F) and should therefore dominate electron transport. Despite the relatively large extension of the molecule, pronounced conductance peaks can be observed. In Figure 5, broad maxima are present at -2.5 , 1 , and $2-3$ eV, where the Fermi level is set to 0 eV. This is due to the delocalized nature of the conducting orbitals, associated with the π -systems of the fullerene and the diazafluorene moieties. In this way, chemical modifications altering the frontier orbital energies should be efficient in tuning electron transport in this system, as these orbitals appear as efficient conduction channels due to their extensive delocalization.

It is interesting to consider how the transmission function at the Fermi level is affected by the different coordination modes of the diazafluorene ligands (Figure 5). As expected, the model considering both diazafluorene groups coordinated by two N atoms (2–2 binding) presents the highest conductance (black solid line). If one of the four N atoms is uncoordinated, one side will have two Au–N bonds and the opposite electrode will present only one bond (2–1 binding). This situation is represented with a red solid line in Figure 5 and is characterized with a significantly lower conductance than the completely coordinated model. As a result, both coordination modes should correspond to different conductance peaks (A and B). If another Au–N bond is broken to yield a 1–1 bonding geometry (red dashed line), we observe a similar conductance to the 2–1 motif. The conductance of both situations is remarkably similar and should be indistinguishable in break-junction experiments (both are assigned to peak B). For the 1–1 bonding geometry, we also verified the effect of the relative orientation of the binding N atoms, calculating the “cis” like conformation (considering the red dashed line geometry as “trans” because the Au–N bond is placed at opposite sides in each anchoring group). Again, the change in conductance is negligible.

Calculations considering weak Au–H contacts are depicted in gray. We observe two clear groups, with the one combining Au–H contacts and Au–N bonds at a markedly larger conductance than the geometry considering only Au–H interactions (dotted gray line). To summarize, we relate peak A with the highest conductance curve in which both diazafluorene groups are coordinated by two N atoms, and peak B with the binding motifs which include only Au–N bonds, where at least one of the binding modes is through only one N atom (red lines). Peak C is consistent with the presence of one Au–H interaction and explains the lower yield for this junction geometry, as it involves weak interactions.

The comparison of the relative values of the calculated transmission functions at the Fermi level and the experimental conductance reinforces this assignment. In log units, the difference between the position of peak A and B ranges from 0.5 to 0.6 , while the calculated values for $T(E)$ between black and red lines ranges from 0.37 to 0.46 . In the experiment, peaks A and C are separated by $1.1-1.3$ log units, comparing well with the difference between the black and the first group of gray curves ($0.82-1.18$). The lowest curve (dashed gray line) is 1.7 log units less conductive than the most conductive mode, and is unlikely to be detected in the experiment. Furthermore, having weak contacts at both gold tips simultaneously leads to a weak binding mode, for which it may be difficult to obtain well-defined conductance plateaus.

The fact that peak B and C each incorporate two different binding can also explain why they are generally broader than

peak A, which only includes one: they comprise different configurations which have slightly different conductance values. This can result in a broadening of the conductance peaks when enough statistics is acquired.

CONCLUSIONS

We measured C_{60} -daf with the MCBJ technique in two different laboratories (Delft and Santiago de Chile). The measurements from both locations agree in identifying three most probable conductance values that we attribute to different configurations between the diazafluorene anchoring groups and the electrodes. Through DFT calculations using the B3LYP density functional, we relate the most conductive peak A with the configurations where both Au–N bonds are present at each side, the middle peak B with the Au–N bonds where at least one of the binding modes is by only one N atom, and the lowest conductance peak C with the presence of one Au–H interaction. The presence of multiple stable arrangements and the relatively low conductance values make this derivative as-is not appealing for employment in single-molecule devices. However, these results show that this geometry is promising and, with some modifications, could open the way to further studies in which the C_{60} backbone can be modified with different functional groups.

ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: [10.1021/acs.chemmater.7b02037](https://doi.org/10.1021/acs.chemmater.7b02037).

Supplementary figures, analysis of additional samples and with different parameters, computational details and synthetic procedures (PDF)

AUTHOR INFORMATION

Corresponding Author

*E-mail: ddulic@ing.uchile.cl. Phone: +56 229784518.

ORCID

Davide Stefani: [0000-0002-9406-9265](https://orcid.org/0000-0002-9406-9265)

Daniel Aravena: [0000-0003-3140-4852](https://orcid.org/0000-0003-3140-4852)

Luis Echegoyen: [0000-0003-1107-9423](https://orcid.org/0000-0003-1107-9423)

Present Address

▲S.L. is currently at Chemistry Department, Xueyuan Beilu 530, Handan Shi, Hebei Sheng 056005, P. R. China

Author Contributions

†D.S. and C.A.G-C. contributed equally.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

The work at TUDelft was supported by the EU through an advanced ERC grant (Mols@Mols); device fabrication was done at the Kavli Nanolab at Delft. The work at University of Chile was supported by Fondecyt Regular Project 1161775 (M.S. and J.L.M.), Fondecyt Regular Project 1140770, EU RISE (DAFNEOX) project SEP-210165479 (D.D.), and CONICYT/Fondecyt Postdoctoral Project 3150674 (C.G.C.). D.A. thanks CONICYT + PAI ‘Concurso nacional de apoyo al retorno de investigadores/as desde el extranjero, convocatoria 2014 82140014’ for financial support. Powered@NLHPC: This research was partially supported by the supercomputing

infrastructure of the NLHPC (ECM-02). L.E. thanks the National Science Foundation [grant CHE-1408865] and the PREM Program [grant DMR-1205302] as well as the Robert A. Welch Foundation [grant AH-0033] for generous financial support. D.S. thanks Riccardo Frisenda for providing the MCBJ schematics in Figure 1b.

REFERENCES

- (1) Balch, A. L.; Olmstead, M. M. Reactions of Transition Metal Complexes with Fullerenes (C60, C70, etc.) and Related Materials. *Chem. Rev.* **1998**, *98*, 2123–2166.
- (2) Matsuo, Y.; Nakamura, E. Selective Multiaddition of Organocopper Reagents to Fullerenes. *Chem. Rev.* **2008**, *108*, 3016–3028.
- (3) Li, C.-Z.; Matsuo, Y.; Nakamura, E. Octupole-Like Supramolecular Aggregates of Conical Iron Fullerene Complexes into a Three-Dimensional Liquid Crystalline Lattice. *J. Am. Chem. Soc.* **2010**, *132*, 15514–15515.
- (4) Ballesteros, B.; de la Torre, G.; Shearer, A.; Hausmann, A.; Herranz, M. o.; Guldi, D. M.; Torres, T. Lanthanide(III) Bis-(phthalocyaninato)-[60]Fullerene Dyads: Synthesis, Characterization, and Photophysical Properties. *Chem. - Eur. J.* **2010**, *16*, 114–125.
- (5) Halim, M.; Kennedy, R. D.; Khan, S. I.; Rubin, Y. Gold(I) Triphenylphosphine Complexes Incorporating Pentaarylfulleride Ligands. *Inorg. Chem.* **2010**, *49*, 3974–3976.
- (6) Zhang, S.; Brown, T. L.; Du, Y.; Shapley, J. R. Metalation of Fullerene (C60) with Pentacarbonylrhenium Radicals. Reversible Formation of C60Re(CO)5. *J. Am. Chem. Soc.* **1993**, *115*, 6705–6709.
- (7) Andersson, C.-H.; Nyholm, L.; Grennberg, H. Synthesis and Characterization of a Ferrocene-Linked Bis-Fullerene[60] Dumbbell. *Dalton Trans.* **2012**, *41*, 2374–2381.
- (8) Grüter, L.; Cheng, F.; Heikkilä, T. T.; González, M. T.; Diederich, F.; Schönenberger, C.; Calame, M. Resonant Tunnelling Through a C60 Molecular Junction in a Liquid Environment. *Nanotechnology* **2005**, *16*, 2143–2148.
- (9) Hirsch, A. The Era of Carbon Allotropes. *Nat. Mater.* **2010**, *9*, 868–871.
- (10) Xiang, D.; Wang, X.; Jia, C.; Lee, T.; Guo, X. Molecular-Scale Electronics: From Concept to Function. *Chem. Rev.* **2016**, *116*, 4318–4440.
- (11) Jeong, H.; Kim, D.; Xiang, D.; Lee, T. High-Yield Functional Molecular Electronic Devices. *ACS Nano* **2017**, *11*, 6511.
- (12) Guldi, D. M.; Illescas, B. M.; Atienza, C. M.; Wielopolski, M.; Martin, N. Fullerene for Organic Electronics. *Chem. Soc. Rev.* **2009**, *38*, 1587–1597.
- (13) Tao, N. J. Electron Transport in Molecular Junctions. *Nat. Nanotechnol.* **2006**, *1*, 173–181.
- (14) Peyghan, A. A.; Soleymanabadi, H.; Moradi, M. Structural and Electronic Properties of Pyrrolidine-Functionalized [60]Fullerenes. *J. Phys. Chem. Solids* **2013**, *74*, 1594–1598.
- (15) Zotti, L. A.; Kirchner, T.; Cuevas, J.-C.; Pauly, F.; Huhn, T.; Scheer, E.; Erbe, A. Revealing the Role of Anchoring Groups in the Electrical Conduction Through Single-Molecule Junctions. *Small* **2010**, *6*, 1529–1535.
- (16) Kristensen, I. S.; Mowbray, D. J.; Thygesen, K. S.; Jacobsen, K. W. Comparative Study of Anchoring Groups for Molecular Electronics: Structure and Conductance of Au-S-Au and Au-NH₂-Au Junctions. *J. Phys.: Condens. Matter* **2008**, *20*, 374101.
- (17) Kaliginedi, V.; Rudnev, A. V.; Moreno-García, P.; Baghernejad, M.; Huang, C.; Hong, W.; Wandlowski, T. Promising Anchoring Groups for Single-Molecule Conductance Measurements. *Phys. Chem. Chem. Phys.* **2014**, *16*, 23529–23539.
- (18) Joachim, C.; Gimzewski, J. K.; Schlittler, R. R.; Chavy, C. Electronic Transparency of a Single C60 Molecule. *Phys. Rev. Lett.* **1995**, *74*, 2102.
- (19) Böhrer, T.; Edtbauer, A.; Scheer, E. Conductance of Individual C60 Molecules Measured with Controllable Gold Electrodes. *Phys. Rev. B: Condens. Matter Mater. Phys.* **2007**, *76*, 125432.
- (20) Parks, J.; Champagne, A.; Hutchison, G.; Flores-Torres, S.; Abruna, H.; Ralph, D. Tuning the Kondo Effect with a Mechanically Controllable Break Junction. *Phys. Rev. Lett.* **2007**, *99*, 026601.
- (21) Kiguchi, M.; Murakoshi, K. Conductance of Single C60 Molecule Bridging Metal Electrodes. *J. Phys. Chem. C* **2008**, *112*, 8140–8143.
- (22) Ohnishi, H.; Kondo, Y.; Takayanagi, K. Quantized Conductance Through Individual Rows of Suspended Gold Atoms. *Nature* **1998**, *395*, 780–783.
- (23) Landauer, R. Electrical Resistance of Disordered One-Dimensional Lattices. *Philos. Mag.* **1970**, *21*, 863–867.
- (24) Martin, C. A.; Ding, D.; Sørensen, J. K.; Bjørnholm, T.; van Ruitenbeek, J. M.; van der Zant, H. S. Fullerene-Based Anchoring Groups for Molecular Electronics. *J. Am. Chem. Soc.* **2008**, *130*, 13198–13199.
- (25) Lörtscher, E.; Geskin, V.; Gotsmann, B.; Fock, J.; Sørensen, J.; Bjørnholm, T.; Cornil, J.; van der Zant, H.; Riel, H. Bonding and Electronic Transport Properties of Fullerene and Fullerene Derivatives in Break-Junction Geometries. *Small* **2013**, *9*, 209–214.
- (26) Leary, E.; Gonzalez, M. T.; Van Der Pol, C.; Bryce, M. R.; Filippone, S.; Martin, N.; Rubio-Bollinger, G.; Agrait, N. Unambiguous One-Molecule Conductance Measurements Under Ambient Conditions. *Nano Lett.* **2011**, *11*, 2236–2241.
- (27) Moreno-García, P.; La Rosa, A.; Kolivoška, V.; Bermejo, D.; Hong, W.; Yoshida, K.; Baghernejad, M.; Filippone, S.; Broekmann, P.; Wandlowski, T.; Martin, N. Charge Transport in C60-Based Dumbbell-Type Molecules: Mechanically Induced Switching Between Two Distinct Conductance States. *J. Am. Chem. Soc.* **2015**, *137*, 2318–2327.
- (28) Ullmann, K.; Coto, P. B.; Leitherer, S.; Molina-Ontoria, A.; Martin, N.; Thoss, M.; Weber, H. B. Single-Molecule Junctions with Epitaxial Graphene Nanoelectrodes. *Nano Lett.* **2015**, *15*, 3512–3518.
- (29) Bilan, S.; Zotti, L. A.; Pauly, F.; Cuevas, J. C. Theoretical Study of the Charge Transport Through C60-Based Single-Molecule Junctions. *Phys. Rev. B: Condens. Matter Mater. Phys.* **2012**, *85*, 205403.
- (30) Géranton, G.; Seiler, C.; Bagrets, A.; Venkataraman, L.; Evers, F. Transport Properties of Individual C60-Molecules. *J. Chem. Phys.* **2013**, *139*, 234701.
- (31) Morita, T.; Lindsay, S. Reduction-Induced Switching of Single-Molecule Conductance of Fullerene Derivatives. *J. Phys. Chem. B* **2008**, *112*, 10563–10572.
- (32) Peng, P.; Li, F.-F.; Bowles, F. L.; Neti, V. S. P. K.; Metta-Magana, A. J.; Olmstead, M. M.; Balch, A. L.; Echegoyen, L. High Yield Synthesis of a New Fullerene Linker and Its Use in the Formation of a Linear Coordination Polymer by Silver Complexation. *Chem. Commun.* **2013**, *49*, 3209–3211.
- (33) Chen, F.; Li, X.; Hihath, J.; Huang, Z.; Tao, N. Effect of Anchoring Groups on Single-Molecule Conductance: Comparative Study of Thiol-, Amine-, and Carboxylic-Acid-Terminated Molecules. *J. Am. Chem. Soc.* **2006**, *128*, 15874–15881.
- (34) Annibale, V. T.; Song, D. Coordination Chemistry and Applications of Versatile 4, 5-Diazafluorene Derivatives. *Dalton Trans.* **2016**, *45*, 32–49.
- (35) Leary, E.; La Rosa, A.; Gonzalez, M. T.; Rubio-Bollinger, G.; Agrait, N.; Martin, N. Incorporating Single Molecules into Electrical Circuits. The Role of the Chemical Anchoring Group. *Chem. Soc. Rev.* **2015**, *44*, 920–942.
- (36) Metzger, R. M. Unimolecular Electronics. *Chem. Rev.* **2015**, *115*, 5056–5115.
- (37) Martin, C. A.; Ding, D.; van der Zant, H. S.; van Ruitenbeek, J. M. Lithographic Mechanical Break Junctions for Single-Molecule Measurements in Vacuum: Possibilities and Limitations. *New J. Phys.* **2008**, *10*, 065008.
- (38) Martin, C. A.; Smit, R. H.; Egmond, R. v.; van der Zant, H. S.; van Ruitenbeek, J. M. A Versatile Low-Temperature Setup for the Electrical Characterization of Single-Molecule Junctions. *Rev. Sci. Instrum.* **2011**, *82*, 053907.

(39) Frisenda, R.; Perrin, M. L.; Valkenier, H.; Hummelen, J. C.; van der Zant, H. S. Statistical Analysis of Single-Molecule Breaking Traces. *Phys. Status Solidi B* **2013**, *250*, 2431–2436.

(40) Seth, C.; Kaliginedi, V.; Suravarapu, S.; Reber, D.; Hong, W.; Wandlowski, T.; Laroche, F.; Broekmann, P.; Royal, G.; Venkatramani, R. Conductance in a Bis-Terpyridine Based Single Molecular Breadboard Circuit. *Chem. Sci.* **2017**, *8*, 1576–1591.

(41) Frisenda, R.; Tarkuç, S.; Galán, E.; Perrin, M. L.; Elkema, R.; Grozema, F. C.; van der Zant, H. S. J. Electrical Properties and Mechanical Stability of Anchoring Groups for Single-Molecule Electronics. *Beilstein J. Nanotechnol.* **2015**, *6*, 1558–1567.

(42) Hong, W.; Manrique, D. Z.; Moreno-Garcia, P.; Gulcur, M.; Mishchenko, A.; Lambert, C. J.; Bryce, M. R.; Wandlowski, T. Single Molecular Conductance of Tolanes: Experimental and Theoretical Study on the Junction Evolution Dependent on the Anchoring Group. *J. Am. Chem. Soc.* **2012**, *134*, 2292–2304.

(43) Etcheverry-Berrios, A.; Olavarría, I.; Perrin, M. L.; Díaz-Torres, R.; Jullian, D.; Ponce, I.; Zagal, J. H.; Pavez, J.; Vásquez, S. O.; van der Zant, H. S. J.; Dulić, D.; Aliaga-Alcalde, N.; Soler, M. Multiscale Approach to the Study of the Electronic Properties of Two Thiophene Curcuminoid Molecules. *Chem. - Eur. J.* **2016**, *22*, 12808–12818.